Date: March 24, 1997

In re application of: Lilip Lau, William M. Hartigan, John J. Frantzen

Serial No.: Divisional of 08/783,097

Filed: January 14, 1997

For: EXPANDABLE STENTS AND METHOD FOR MAKING SAME

THE COMMISSIONER OF PATENTS AND TRADEMARKS

Washington, D.C. 20231

The state of the s

smitted herewith is an amendment in the above-identified application:

Small entity status of this application under 37 CFR 1.9 and 1.27 has been established by a verified statement previously submitted.

A verified statement to establish small entity status under 37 CFR 1.9 and 1.27 is enclosed. No additional fee is required.

fee has been calculated as shown below:

	COL. (1)		COL. (2)	COL. (3)		
	CLAIMS REMAINING AFTER AMENDMENT		HIGHEST NO. PREVIOUSLY PAID FOR	PRESENT EXTRA		
TAL	• 8	MINUS	·· 20	٠ -٥-		
EP.	• 1	MINUS	*** 3	• -0-		
FIRS	FIRST PRESENTATION OF MULTIPLE DEP. CLAIM					

SMALL	ENTITY
RATE	FEE
X \$ 11	\$
X \$ 39	\$
+ \$125	\$
1 MO. EXT. \$ 55	\$
2 MO. EXT. \$ 190	\$
з мо. ехт. \$ 450	\$
TOTAL ADDL. FEE	\$

OTHER THAN A SMALL ENTITY					
RATE	ADDITIONAL FEE				
X \$ 22	\$				
X \$ 80	\$				
+ \$250	\$				
1 мо. ехт. \$ 110	\$				
2 MO. EXT. \$ 380	\$				
з мо. ехт. \$ 900	\$				
TOTAL ADDL. FEE	\$ -0-				

*	If the entry in Col. 1 is less than the entry in Col. 2, write "0" in Col. 3.
* *	If the "Highest Number Previously Paid For" IN THIS SPACE is less than 20, write "20" in this space.

	Please charge my Deposit Account No. 06-2425 the amount of \$ A duplicate of this sheet is enclosed.
	A check in the amount of \$ to cover the filing fee is enclosed.

The Commissioner is hereby authorized to charge payment of the following fees associated with this communication or credit any overpayment to Deposit Account No. 06-2425. A duplicate copy of this sheet is enclosed.

☐ Any patent application processing fees under 37 CFR 1.17.

FULWIDER PATTON LEE & UTECHT, LLP

Any additional filing fees required under 37 CFR 1.16.

Attorneys at Law 10877 Wilshire Boulevard, Tenth Floor Los Angeles, California 90024

Respectfully submitted,

JSN:jeb

Express Mail No. EM375441217US



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Continuing Application under 37 CFR 1.60

Docket Number:	Anticipated Classification of	Prior application:		
ACS 42595	this Application: <u>Class</u> <u>Subclass</u>	Examiner Art Unit C. Bennett 3307		
		C. Bennett 33U7		

Box PATENT APPLICATION ASSISTANT COMMISSIONER FOR PATENTS Washington, D.C. 20231

This is	a req	uest for fili	nga[] (continuati	on [x] div	isional	applicat	cion	under 37	CFR	1.60,
of pending p	rior .	Application N	io. <u>08/783</u>	3,097	, filed o	on <u>Ja</u>	<u>nuary 14</u>	<u>, 199</u>	97_, of		
		iam Hartigan,				(s) C	urrently	of	record	in	prior
- in tipe	for	EXPANDABLE	STENTS AN	ND METHOD	FOR MAKING	SAME					
application/	101										·

[X] Enclosed is a copy of the prior application, including the oath or declaration as originally filed.

I hereby verify that the attached papers are a true copy of prior Appln. No. <u>08/783,097</u>, as originally filed on <u>January 14, 1997</u> and further that this statement was made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

- [] Verified Small Entity Status form(s):
 [] enclosed, [] will follow, [] filed in prior application and copy(s) enclosed.
- [X] The filing fee is calculated below:

CLAIMS AS FILED <u>IN PRIOR APPLICATION</u>, LESS ANY CLAIMS CANCELLED BY AMENDMENT BELOW.

For	Number filed		Numbe extra		Rate		Fee_
Total Claims	8 -	20 =	-0-	<u> </u>	\$22.00	= \$	
Independent claims	1 -	3 =	-0-	. Х	\$80.00	= \$	<u> </u>
Multiple Dependent	Claim Fee				\$260.00	= \$	
Basic fee							<u>770.00</u>
Total of above Cal	culations :	=				= \$	770.00
Reduction by % for	filing by	smal	l entity	(Note	:		
37 CFR 1.9, 1.	27. 1.28)				Less	= \$	
37 CFR 1.37 1.	<u> </u>			TOTA	AL = \$		770.00

- 4. [X] A check in the amount of \$ 770.00 is enclosed.
- 5. [X] The Commissioner is hereby authorized to charge any additional fees which may be required in connection with this filing, or credit any overpayment, to Account No. 06-2425. A duplicate copy of this sheet is enclosed.

PAGE 1 OF 2

		PATENT Atty. Docket No.
6.	[X]	Cancel in this application original claims <u>1 thru 24</u> of the prior application before calculating the filing fee. (At least one original independent claim must be retained for filing purposes.)
7.	[X]	Amend the specification by inserting before the first line the sentence:This is a [] continuation, [X] division, of Application No
8.	[]	Transfer the drawings from the prior application to this application and abandon said prior application as of the filing date accorded this application. A duplicate copy of this sheet is enclosed for filing in the prior application file. (May only be used if signed by person authorized by Section 1.138 and before payment of base issue fee.)
8a.	[X]	New drawings [] formal [X] informal are enclosed.
8b.	[]	Priority of Application No, filed on in is claimed under 35 U.S.C. 119.
8c.	[]	The certified copy has been filed in prior Application No, filed,
<u></u>	[X]	The prior application is assigned of record to <u>ADVANCED CARDIOVASCULAR</u> SYSTEMS, INC.
9 0 10 11 11 11 11 11 11 11 11 11 11 11 1	£ % 3	A preliminary amendment is enclosed. (Claims added by this amendment have been properly numbered consecutively beginning with the number next following the highest numbered original claim in the prior application.)
摚.	[X]	The power of attorney in the prior application is to:
S	Crai	g B. Bailey, Reg. No. 28,786; Richard A. Bardin, Reg. No. 20,365;
Company Company	Gilb	ert G. Kovelman, Reg. No. 19,552; and John S. Nagy, Reg. No. 30,664
	all	ert G. Kovelman, Req. No. 19,552; and John S. Nagy, Req. No. 30,664 of FULWIDER PATTON LEE & UTECHT, LLP (name and registration number) Wilshire Blvd, 10th Floor, Los Angeles, California 90024.
		(name and registration number)
all of	10877	Wilshire Blvd, 10th Floor, Los Angeles, California 90024.
11a.	[X]	The power appears in the original papers in the prior application.
11b.	[]	Since the power does not appear in the original papers, a copy of the power in the prior application is enclosed.
11c.	[X]	Address all future communications to: <u>John S. Nagy, Esq.</u> , FULWIDER PATTON LEE & UTECHT, LLP, 10877 Wilshire Blvd., 10th Floor, Los Angeles, California 90024.
11d.	[X]	Address all telephone inquiries to John S. Nagy at the below listed telephone number. (May only be completed by applicant, or attorney or agent of record.)
	(1	3/24/97 John Nagy (Signature)
FULWID 10877 Los An Teleph	Wilshi geles, one No	



IN THE UNITED STATES PATENT & TRADEMARK OFFICE

In re the application of) Examiner: C. Bennett
Inventors: Lilip Lau, William Hartigan, John J.) Group Art Unit: 3307
Frantzen) Docket No. ACS 42595 (3808.2)
Division of U.S. Serial No. 08/783,097	
Filed: Concurrently)
For: EXPANDABLE STENTS AND METHOD FOR MAKING SAME) Los Angeles, California) March 24, 1997

PRELIMINARY AMENDMENT

Assistant Commissioner for Patents Washington, D.C. 20231

Dear Sir:

This Preliminary Amendment is being filed concurrently with the application that is a division of U.S. Serial No. 08/783,097 filed January 14, 1997. Please enter and consider this Preliminary Amendment in examination of the application.

IN THE SPECIFICATION:

At page 1, line 2, after the word "application" insert the following:

--is a division of U.S. Serial No. 08/783,097, filed January 14, 1997, which is a division of U.S. Serial No.

08/556,516, filed November 13, 1995, which is a division of U.S. Serial No. 08/281,790, filed July 28, 1994, now U.S. Patent No. 5,514,154, which--

IN THE CLAIMS:

Please cancel claims 2-24 without prejudice.

Please add the following new claims:

25. A method of chemically etching a serpentine pattern on a metallic member to form an intravascular stent, comprising:

applying a coating resistive to chemical etching to a metallic surface of the metallic member;

selectively removing portions of the resistive coating form the metallic surface thereby providing exposed portions of the metallic surface and protected portions of the metallic surface, the protected portions of the metallic surface forming the serpentine pattern;

exposing the metallic surface to a chemical etchant solution thereby removing all of the exposed portions of the metallic surface; and

means for removing the resistive coating and polishing the metal surface to provide a uniform surface finish thereby forming the serpentine pattern of the stent.

26. The method of claim 25, wherein the step of removing the resistive coating is performed by a laser.

- 27. The method of claim 26, wherein the laser is operated in a pulsed mode for removing the resistive coating.
- $28. \ \ \mbox{The method of claim 27, wherein the pulse length time is about .3 mS.$
- 29. The method of claim 26, wherein the laser is operated so that it removes only the resistive coating, and not the metallic surface of the metallic member.
- 30. The method of claim 25, wherein the metallic surface of the metallic member, prior to the step of applying the resistive coating, is flat.
- 31. The method of claim 25, wherein the metallic surface, prior to the application of the resistive coating, is curved.
- 32. The method of claim 25, wherein the means for removing the resistive coating and polishing the metallic surface includes electrochemically polishing the metallic member in an acidic aqueous solution.

REMARKS

This application is a division of U.S. Serial No. 08/783,097, filed January 14, 1997. Claims 2-24 have been cancelled without prejudice and claims 25-32 have been added by this Preliminary Amendment. No new matter is believed to be presented as all of the new claims are fully supported by the specification and the drawings. Thus, claims 25-32 are pending in the application and early consideration and allowance is earnestly solicited.

Respectfully submitted,
FULWIDER PATTON LEE & UTECHT, LLP

By:

John 8. Nagy

Registration No. 30,664

JSN:jeb

10877 Wilshire Boulevard, Tenth Floor Los Angeles, California 90024 (310) 824-5555



APPLICATION

of

LILIP LAU

WILLIAM M. HARTIGAN

JOHN J. FRANTZEN

for

UNITED STATES LETTERS PATENT

on

EXPANDABLE STENTS AND METHOD FOR MAKING SAME

Docket No. ACS 35765 (3804.1)

Sheets of Drawing: Four (4)

Attorneys
FULWIDER PATTON LEE & UTECHT
10877 Wilshire Boulevard, 10th Floor
Los Angeles, California 90024

EXPANDABLE STENTS AND METHOD FOR MAKING SAME



RELATED APPLICATIONS

This application is a continuation-in-part of copending U.S. patent application U.S. Serial No. 08/164,986 filed December 9, 1993, which is a continuation application of U.S. Serial No. 07/783,558 filed October 28, 1991, now abandoned.

BACKGROUND OF THE INVENTION

This invention relates to expandable endoprosthesis devices, generally called stents, which are adapted to be implanted into a patient's body lumen, such as blood vessel, to maintain the patency thereof. These devices are very useful in the treatment of atherosclerotic stenosis in blood vessels.

Stents are generally tubular-shaped devices which function to hold open a segment of a blood vessel or other anatomical lumen. They are particularly suitable for use to support and hold back a dissected arterial lining which can occlude the fluid passageway therethrough.

Further details of prior art stents can be found in U.S. Patent 3,868,956 (Alfidi et al.); U.S. Patent 4,512,338

20 (Balko et al.); U.S. Patent 4,553,545 (Maass et al.); U.S. Patent 4,733,665 (Palmaz); U.S. Patent 4,762,128 (Rosenbluth); U.S. Patent 4,800,882 (Gianturco); U.S. Patent 4,856,516 (Hillstead); and U.S. Patent 4,886,062 (Wiktor), which are hereby incorporated herein in their entirety by reference thereto.

Various means have been described to deliver and implant stents. One method frequently described for delivering a stent to a desired intraluminal location includes mounting the expandable stent on an expandable member, such as a balloon, provided on the distal end of an intravascular catheter, advancing the catheter to the desired location within the patient's body lumen, inflating the balloon on the catheter

to expand the stent into a permanent expanded condition and then deflating the balloon and removing the catheter. One of the difficulties encountered using prior stents involved maintaining the radial rigidity needed to hold open a body 5 lumen while at the same time maintaining the longitudinal flexibility of the stent to facilitate its delivery.

What has been needed and heretofore unavailable is a stent which has a high degree of flexibility so that it can be advanced through tortuous passageways and can be readily 10 expanded and yet have the mechanical strength to hold open the body lumen into which it expanded. The present invention satisfies this need.

SUMMARY OF THE INVENTION

The present invention is directed to an expandable stent which is relatively flexible along its longitudinal axis to facilitate delivery through tortuous body lumens, but which is stiff and stable enough radially in an expanded condition to maintain the patency of a body lumen such as an artery when implanted therein.

The stent of the invention generally includes a plurality of radially expandable cylindrical elements which are relatively independent in their ability to expand and to flex relative to one another. The individual radially expandable cylindrical elements of the stent are dimensioned so as to be 25 longitudinally shorter than their own diameters. Interconnecting elements or struts extending between adjacent cylindrical elements provide increased stability and a preferable position to prevent warping of the stent upon the expansion thereof. The resulting stent structure is a series 30 of radially expandable cylindrical elements which are spaced longitudinally close enough so that small dissections in the wall of a body lumen may be pressed back into position against the lumenal wall, but not so close as to compromise the longitudinal flexibilities of the stent. The individual

25

cylindrical elements may rotate slightly relative to adjacent cylindrical elements without significant deformation, cumulatively giving a stent which is flexible along its length and about its longitudinal axis but is still very stiff in the radial direction in order to resist collapse.

The stent embodying features of the invention can be readily delivered to the desired lumenal location by mounting it on an expandable member of a delivery catheter, for example a balloon, and passing the catheter-stent assembly through the body lumen to the implantation site. A variety of means for securing the stent to the expandable member on the catheter for delivery to the desired location are available. It is presently preferred to compress the stent onto the balloon. Other means to secure the stent to the balloon include providing ridges or collars on the inflatable member to restrain lateral movement, or using bioresorbable temporary adhesives.

The presently preferred structure for the expandable cylindrical elements which form the stents of the present invention generally circumferential undulating pattern, e.g. serpentine. The transverse cross-section of the undulating component of the cylindrical element is relatively small and preferably has an apect ratio of about two to one to about 0.5 to one. A one to one apect ratio has been found particularly suitable. The open reticulated structure of the stent allows for the perfusion of blood over a large portion of the arterial wall which can improve the healing and repair of a damaged arterial lining.

The radial expansion of the expandable cylinder
deforms the undulating pattern thereof similar to changes in a
waveform which result from decreasing the waveform's amplitude
and the frequency. Preferably, the undulating patterns of the
individual cylindrical structures are in phase with each other
in order to prevent the contraction of the stent along its
length when it is expanded. The cylindrical structures of the
stent are plastically deformed when expanded (except with NiTi

alloys) so that the stent will remain in the expanded condition and therefore they must be sufficiently rigid when expanded to prevent the collapse thereof in use. During expansion of the stent, portions of the undulating pattern will tip outwardly resulting in projecting members on the outer surface of the expanded stent. These projecting members tip radially outwardly from the outer surface of the stent and embed in the vessel wall and help secure the expanded stent so that it does not move once it is implanted.

With superelastic NiTi alloys, the expansion occurs when the stress of compression is removed so as to allow the phase transformation from austenite back to martensite and as a result the expansion of the stent.

The elongated elements which interconnect adjacent 15 cylindrical elements should have a transverse cross-section similar to the transverse dimensions of the undulating components of the expandable cylindrical elements. The interconnecting elements may be formed in a unitary structure with the expandable cylindrical elements from the same intermediate product, such as a tubular element, or they may be formed independently and connected by suitable means, such as by welding or by mechanically securing the ends of the interconnecting elements to the ends of the expandable cylindrical elements. Preferably, all of the interconnecting elements of a stent are joined at either the peaks or the valleys of the undulating structure of the cylindrical elements which for the stent. In this manner there is no shortening of the stent upon expansion.

The number and location of elements interconnecting
adjacent cylindrical elements can be varied in order to develop
the desired longitudinal flexibility in the stent structure
both in the unexpanded as well as the expanded condition.
These properties are important to minimize alteration of the
natural physiology of the body lumen into which the stent is
implanted and to maintain the compliance of the body lumen
which is internally supported by the stent. Generally, the

25

30

greater the longitudinal flexibility of the stent, the easier and the more safely it can be delivered to the implantation site.

In a presently preferred embodiment of the invention 5 the stent is conveniently and easily formed by coating stainless steel tubing with a material resistant to chemical etching, removing portions of the coating to expose portions of underlying tubing which are to be removed to develop the desired stent structure. The exposed portions of the tubing 10 are removed by chemically etching from the tubing exterior leaving the coated portion of the tubing material in the desired pattern of the stent structure. The etching process develops smooth openings in the tubing wall without burrs or other artifacts which are characteristic of mechanical or laser machining processes in the small sized products contemplated. Moreover, a computer controlled laser patterning process to remove the chemical resistive coating makes photolithography technology adaptable to the manufacture of these The forming of a mask in the extremely small sizes products. needed to make the small stents of the invention would be a most difficult task. A plurality of stents can be formed from one length of tubing by repeating the stent pattern and providing small webs or tabs to interconnect the stents. After the etching process, the stents can be separated by severing the small webs or tabs which connect them.

Other features and advantages of the invention will become more apparent from the following detailed description of the invention. When taken in conjunction with the accompanying exemplary drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

FIGURE 1 is an elevational view, partially in section, of a stent embodying features of the invention which is mounted on a delivery catheter and disposed within a damaged artery.

- FIG. 2 is an elevational view, partially in section, similar to that shown in FIG. 1 wherein the stent is expanded within a damaged artery, pressing the damaged lining against the arterial wall.
- FIG. 3 is an elevational view, partially in section showing the expanded stent within the artery after withdrawal of the delivery catheter.
- FIG. 4 is a perspective view of a stent embodying features of the invention in an unexpanded state, with one end of the stent being shown in an exploded view illustrate the details thereof.
 - FIG. 5 is a plan view of a flattened section of a stent of the invention which illustrates the undulating pattern of the stent shown in FIG. 4.
- FIG. 6 is a schematic representation of equipment for selectively removing coating applied to tubing in the manufacturing of the stents of the present invention.
- FIGS. through 10 are perspective schematically illustrating various configurations of 20 interconnective element placement between the expandable cylindrical elements of the stent.
- FIG. 11 is a plan view of a flattened section of a stent illustrating an alternate undulating pattern in the expandable cylindrical elements of the stent which are out of phase.
 - FIG. 12 is an enlarged partial view of the stent of FIG. 5 with the various members slightly expanded.

20

FIG. 13 is a perspective view of the stent of FIG. 4 after it is fully expanded depicting some members projecting radially outwardly.

FIG. 14 is an enlarged, partial perspective view of one U-shaped member with its tip projecting outwardly after expansion.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

of the invention which is mounted onto a delivery catheter 11. The stent generally comprises a plurality of radially expandable cylindrical elements 12 disposed generally coaxially and interconnected by elements 13 disposed between adjacent cylindrical elements. The delivery catheter 11 has an expandable portion or balloon 14 for expanding of the stent 10 within an artery 15. The artery 15, as shown in FIG. 1 has a dissected lining 16 which has occluded a portion of the arterial passageway.

The delivery catheter 11 onto which the stent 10 is mounted, is essentially the same as a conventional balloon dilatation catheter for angioplasty procedures. The balloon 14 may be formed of suitable materials such as polyethylene, polyethylene terephthalate, polyvinyl chloride, nylon and ionomers such as Surlyn® manufactured by the Polymer Products Division of the Du Pont Company. Other polymers may also be In order for the stent 10 to remain in place on the balloon 14 during delivery to the site of the damage within the artery 15, the stent 10 is compressed onto the balloon. retractable protective delivery sleeve 20 as described in copending applications Serial No. 07/647,464 filed on april 25, 1990 and entitled STENT DELIVERY SYSTEM may be provided to further ensure that the stent stays in place on the expandable portion of the delivery catheter 11 and prevent abrasion of the body lumen by the open surface of the stent 20 during delivery

10

to the desired arterial location. Other means for securing the stent 10 onto the balloon 14 may also be used, such as providing collars or ridges on the ends of the working portion, i.e. the cylindrical portion, of the balloon.

Each radially expandable cylindrical element 12 of the stent 10 may be independently expanded. Therefore, the balloon 14 may be provided with an inflated shape other than cylindrical, e.g. tapered, to facilitate implantation of the stent 10 in a variety of body lumen shapes.

In a preferred embodiment, the delivery of the stent 10 is accomplished in the following manner. The stent 10 is first mounted onto the inflatable balloon 14 on the distal extremity of the delivery catheter 11. The balloon 14 is slightly inflated to secure the stent 10 onto the exterior of the balloon. The catheter-stent assembly is introduced within the patient's vasculature in a conventional Seldinger technique through a guiding catheter (not shown). A guidewire 18 is disposed across the damaged arterial section with the detached or dissected lining 16 and then the catheter-stent assembly is advanced over a guidewire 18 within the artery 15 until the stent 10 is directly under the detached lining 16. The balloon 14 of the catheter is expanded, expanding the stent 10 against the artery 15, which is illustrated in FIG. 2. While not shown in the drawing, the artery 15 is preferably expanded slightly by the expansion of the stent 10 to seat or otherwise fix the stent 10 to prevent movement. In some circumstances during the treatment of stenotic portions of an artery, the artery may have to be expanded considerably in order to facilitate passage of blood or other fluid therethrough.

The stent 10 serves to hold open the artery 15 after the catheter 11 is withdrawn, as illustrated by FIG. 3. Due to the formation of the stent 10 from elongated tubular member, the undulating component of the cylindrical elements of the stent 10 is relatively flat in transverse cross-section, so that when the stent is expanded, the cylindrical elements are pressed into the wall of the artery 15 and as a result do not

interfere with the blood flow through the artery 15. cylindrical elements 12 of stent 10 which are pressed into the wall of the artery 15 will eventually be covered with endothelial cell growth which further minimizes blood flow The undulating portion of the cylindrical 5 interference. sections 12 provide good tacking characteristics to prevent stent movement within the artery. Furthermore, the closely spaced cylindrical elements 12 at regular intervals provide uniform support for the wall of the artery 15, and consequently 10 are well adapted to tack up and hold in place small flaps or dissections in the wall of the artery 15 as illustrated in FIGS. 2 and 3.

FIG. 4 is an enlarged perspective view of the stent 10 shown in FIG. 1 with one end of the stent shown in an exploded view to illustrate in greater detail the placement of interconnecting elements 13 between adjacent radially · expandable cylindrical elements 12. Each pair of interconnecting elements 13 on one side of a cylindrical element 12 are preferably placed to achieve maximum flexibility for a stent. In the embodiment shown in FIG. 4 the stent 10 has three interconnecting elements 13 between adjacent radially expandable cylindrical elements 12 which are 120 degrees apart. Each pair of interconnecting elements 13 on one side of a cylindrical element 12 are offset radially 60 degrees from the pair on the other side of the cylindrical element. alternation of the interconnecting elements results in a stent which is longitudinally flexible in essentially all directions. Various configurations for the placement of interconnecting elements are possible, and several examples are illustrated 30 schematically in FIGS. 7-10. However, as previously mentioned, all of the interconnecting elements of an individual stent should be secured to either the peaks or valleys of the undulating structural elements in order to prevent shortening of the stent during the expansion thereof.

35 FIG. 10 illustrates a stent of the present invention wherein three interconnecting elements 12 are disposed between

25

30

radially expandable cylindrical elements 11. The interconnecting elements 12 are distributed radially around the circumference of the stent at a 120-degree spacing. Disposing four or more interconnecting elements 13 between adjacent 5 cylindrical elements 12 will generally give rise to the same considerations discussed above for two and three interconnecting elements.

The properties of the stent 10 may also be varied by alteration of the undulating pattern of the cylindrical elements 13. FIG. 11 illustrates an alternative stent structure in which the cylindrical elements are in serpentine patterns but out of phase with adjacent cylindrical elements. The particular pattern and how many undulations per unit of length around the circumference of the cylindrical element 13, or the amplitude of the undulations, are chosen to fill particular mechanical requirements for the stent such as radial stiffness.

The number of undulations may also be varied to accommodate placement of interconnecting elements 13, e.g. at the peaks of the undulations or along the sides of the undulations as shown in FIGS. 5 and 11.

In keeping with the invention, and with reference to FIGS. 4 and 12-14, cylindrical elements 12 are in the form of a serpentine pattern 30. As previously mentioned, each cylindrical element 12 is connected by interconnecting elements 13. Serpentine pattern 30 is made up of a plurality of U-shaped members 31, W-shaped members 32, and Y-shaped members 33, each having a different radius so that expansion forces are more evenly distributed over the various members.

As depicted in FIGS. 13 and 14, after cylindrical elements 12 have been radially expanded, outwardly projecting edges 34 are formed. That is, during radial expansion U-shaped members 31 will tip outwardly thereby forming outwardly projecting edges. These outwardly projecting edges provide for a roughened outer wall surface of stent 10 and assist in implanting the stent in the vascular wall by embedding into the

vascular wall. In other words, outwardly projecting edges embed into the vascular wall, for example artery 15, as depicted in FIG. 3. Depending upon the dimensions of stent 10 and the thickness of the various members making up the 5 serpentine pattern 30, any of the U-shaped members 31, W-shaped members 32, and Y-shaped members 33 can tip radially outwardly to form a projecting edge 34. It is most likely and preferred that U-shaped members 31 tip outwardly since they do not join with any connecting member 13 to prevent them from expanding outwardly.

The stent 10 of the present invention can be made in many ways. However, the preferred method of making the stent is to coat a thin-walled tubular member, such as stainless steel tubing, with a material which is resistive to chemical etchants, remove portions of the coating to expose underlying tubing which is to be removed but to leave coated portions of the tubing in the desired pattern for the stent so that subsequent etching will remove the exposed portions of the metallic tubing, but will leave relatively untouched the portions of the metallic tubing which are to form the stent. The coated portion of the metallic tube is in the desired shape for the stent. An etching process avoids the necessity of removing burrs or slag inherent in conventional or laser machining process. It is preferred to remove the etchantresistive material by means of a machine-controlled laser as illustrated schematically in FIG. 6.

A coating is applied to a length of tubing which, when cured, is resistive to chemical etchants. Photoresist" made by the Shipley Company in San 30 California, is an example of suitable commercially available photolithographic coatings. The coating is preferably applied by electrophoretic deposition.

To ensure that the surface finish is reasonably uniform, one of the electrodes used for the electrochemical polishing is a doughnut-shaped electrode which is placed about the central portion of the tubular member.

The tubing may be made of suitable biocompatible stainless steel, material such as titanium, tantalum. superelastic NiTi alloys and even high strength thermoplastic polymers. The stent diameter is very small, so the tubing from 5 which it is made must necessarily also have a small diameter. Typically the stent has an outer diameter on the order of about 0.06 inch in the unexpanded condition, the same outer diameter of the tubing from which it is made, and can be expanded to an outer diameter of 0.1 inch or more. The wall thickness of the tubing is about 0.003 inch. In the instance when the stent was plastic, it would have to be heated within the arterial site where the stent is expanded to facilitate the expansion of the stent. Once expanded, it would then be cooled to retain its The stent may be conveniently heated by expanded state. 15 heating the fluid within the balloon or the balloon directly by a suitable system such as disclosed in a co-pending application Serial No. 07/521,337, filed January 26, 1990 entitled DILATATION CATHETER ASSEMBLY WITH HEATED BALLOON which is incorporated herein in its entirety by reference. The stent may also be made of materials such as superelastic NiTi alloys such as described in co-pending application Serial 07/629,381, filed December 18, 1990, entitled SUPERELASTIC GUIDING MEMBER which is incorporated herein in its entirety by reference. In this case the stent would be formed full size but deformed (e.g. compressed) into a smaller diameter onto the balloon of the delivery catheter to facilitate transfer to a desired intraluminal site. The stress induced by the deformation transforms the stent from a martensite phase to an austenite phase and upon release of the force, when the stent 30 reaches the desired intraluminal location, allows the stent to expand due to the transformation back to the martensite phase.

Referring to FIG. 6, the coated tubing 21 is put in a rotatable collet fixture 22 of a machine controlled apparatus 23 for positioning the tubing 21 relative to a laser 24. According to machine-encoded instructions, the tubing 21 is rotated and moved longitudinally relative to the laser 24 which

is also machine controlled. The laser selectively removes the etchant-resistive coating on the tubing by ablation and a pattern is formed such that the surface of the tube that is to be removed by a subsequent chemical etching process is exposed. The surface of the tube is therefore left coated in the discrete pattern of the finished stent.

A presently preferred system for removing the coating on the tubing includes the use an 80-watt CO_2 laser, such as a Coherent Model 44, in pulse mode (0.3 mS pulse length); 48 mA 10 key current and 48 W key power with 0.75 W average power, at 100 Hz; Anorad FR=20; 12.5 Torr; with no assist gas. pressure air is directed through the fine focus head to ensure that no vapor contacts the lens. The assist gas jet assembly on the laser unit may be removed to allow a closer proximity of the fine focus head and the collet fixture. Optimum focus is set at the surface of the tubing. Cured photo-resist coating readily absorbs the energy of the CO2 wavelength, so that it can be readily removed by the laser. A coated 4-inch length of 0.06 inch stainless steel tubing is preferred and four stents can be patterned on the length of tubing. Three tabs or webs between stents provide good handling characteristics for the tubing after the etching process.

The process of patterning the resistive coating on the stent is automated except for loading and unloading the length of tubing. Referring again to FIG. 6 it may be done, for example, using a CNC-opposing collet fixture 22 for axial rotation of the length of tubing, in conjunction with a CNC X/Y table 25 to move the length of tubing axially relative to a machine-controlled laser as described. The entire space between collets can be patterned using the CO₂ laser set-up of the foregoing example. The program for control of the apparatus is dependent on the particular configuration used and the pattern to be ablated in the coating, but is otherwise conventional.

This process makes possible the application of present photolithography technology in manufacturing the

25

5

stents. While there is presently no practical way to mask and expose a tubular photo-resist coated part of the small size required for making intravascular stents, the foregoing steps eliminate the need for conventional masking techniques.

After the coating is thus selectively ablated, the tubing is removed from the collet fixture 22. Next, wax such at ThermoCote N-4 is heated to preferably just above its melting point, and inserted into the tubing under vacuum or pressure. After the wax has solidified upon cooling, it is 10 reheated below its melting point to allow softening, and a smaller diameter stainless steel shaft is inserted into the softened wax to provide support. The tubing is then etched chemically in a conventional manner. After cutting the tabs connecting the stents any surface roughness or debris from the 15 tabs is removed. The stents are preferably electrochemically polished in an acidic aqueous solution such as a solution of ELECTRO-GLO #300, sold by the ELECTRO-GLO CO., Inc. in Chicago, Illinois, which is a mixture of sulfuric acid, carboxylic acids, phosphates, corrosion inhibitors and a biodegradable surface active agent. The bath temperature is maintained at about 110-135 degrees F. and the current density is about 0.4 to about 1.5 amps per in.2 Cathode to anode area should be at least about two to one. The stents may be further treated if desired, for example by applying a biocompatible coating.

While the invention has been illustrated and described herein in terms of its use as an intravascular stent, it will be apparent to those skilled in the art that the stent can be used in other instances such as to expand prostatic urethras in cases of prostate hyperplasia. Other modifications and improvements may be made without departing from the scope of the invention.

Other modifications and improvements can be made to the invention without departing from the scope thereof.

1.5

WHAT IS CLAIMED IS:

- 1. A longitudinally flexible stent for implanting in a body lumen, comprising:
- a plurality of cylindrical elements which are independently expandable in the radial direction and which are interconnected so as to be generally aligned on a common longitudinal axis;
 - a plurality of connecting elements for interconnecting said cylindrical elements, said connecting elements configured to interconnect only said cylindrical elements that are adjacent to each other; and
 - an outer wall surface on said cylindrical elements, said outer wall surface having a plurality of outwardly projecting edges which form as said stent is expanded radially outwardly from a first diameter to a second, enlarged diameter.
 - 2. The stent of claim 1, wherein said outer wall surface is substantially smooth when said stent in said first diameter configuration and said outwardly projecting edges form only as said stent is expanded radially outwardly from said first diameter to said second, enlarged diameter.
 - 3. The stent of claim 1, wherein said plurality of outwardly projecting edges extend a distance from said outer wall surface sufficient enough to embed in the vascular wall of the body lumen in order to more firmly attach said stent to the vascular wall.
 - 4. The stent of claim 1, wherein said plurality of cylindrical elements include a plurality of peaks and valleys having a serpentine pattern.

- 5. The stent of claim 4, wherein said plurality of peaks and valleys include a plurality of U-shaped members, a plurality of Y-shaped members, and a plurality of W-shaped members, some of said U-shaped, Y-shaped, and W-shaped members being interconnected.
 - 6. The stent of claim 5, wherein at least some of said plurality of said U-shaped members tip radially outwardly to form said outwardly projecting edges upon radial expansion of said stent.
 - 7. The stent of claim 5, wherein at least some of said plurality of U-shaped, W-shaped, and Y-shaped members tip radially outwardly to form said outwardly projecting edges upon radial expansion of said stent.
 - 8. The stent of claim 1, wherein said cylindrical elements are capable of retaining their expanded condition upon the expansion thereof.
 - 9. The stent of claim 1, wherein said stent is formed of a biocompatible material selected from the group of materials consisting of stainless steel, tantalum, NiTi alloys, and thermoplastic polymers.
 - 10. The stent of claim 1, wherein said stent is formed from a single piece of tubing.

- 11. The stent of claim 1, wherein said stent is coated with a biocompatible coating.
 - 12. A longitudinally flexible stent, comprising:
- a plurality of cylindrical elements which are independently expandable in the radial direction and which are interconnected so as to be concentrically aligned on a common longitudinal axis; and
- a plurality of generally parallel connecting elements for interconnecting said cylindrical elements, said connecting elements configured to interconnect only said cylindrical elements that are adjacent to each other, so that said stent, when expanded radially outwardly, retains its overall length without appreciable shortening.
- 13. The stent of claim 12, wherein said cylindrical elements are capable of retaining their expanded condition upon the expansion thereof.
- 14. The stent of claim 12, wherein said radially expandable cylindrical elements in an expanded condition have a length less than the diameter thereof.
- 15. The stent of claim 14, wherein said stent is formed of a biocompatible material selected from the group consisting of stainless steel, tantalum, super-elastic NiTi alloys, and thermoplastic polymers.
- 16. The stent of claim 12, wherein said connecting elements between adjacent cylindrical elements are in axial alignment.

- 17. The stent of claim 12, wherein said connecting elements between adjacent cylindrical elements are circumferentially displaced with respect to said longitudinal axis.
- 18. The stent of claim 17, wherein the circumferential displacement of said connecting elements between adjacent cylindrical elements is uniform.
- 19. The stent of claim 12, wherein there are up to four of said connecting elements disposed between adjacent radially expandable cylindrical elements.
- 20. The stent of claim 12, wherein said radially expandable cylindrical elements and said connecting elements are made of the same material.
- 21. The stent of claim 12, wherein said stent is formed from a single piece of tubing.
- 22. The stent of claim 12, wherein the stent is coated with a biocompatible coating.

23. A kit of parts, comprising:

an elongated stent delivery catheter having a proximal end and a distal end, and an expandable member on the distal end; and

a longitudinally flexible stent which is adapted to be slidably mounted onto the expandable member of said

catheter and which comprises a plurality of cylindrical elements which are independently expandable in the radial direction and which are interconnected so as to be concentrically aligned on a common longitudinal axis, wherein each said element is formed of a single elongated structural member forming a serpentine pattern having undulations with peaks and valleys, said elements being interconnected by a plurality of generally parallel interconnecting members between adjacent elements, each said interconnecting member configured to interconnect only said cylindrical elements that are adjacent to each other.

24. A method of transluminally implanting a longitudinally flexible stent in a body lumen, said stent having a plurality of cylindrical elements which are independently expandable in the radial direction and which are interconnected so as to be concentrically aligned on a common longitudinal axis, wherein each said cylindrical element is interconnected a plurality of generally parallel connecting members between adjacent elements, the method comprising the steps of:

placing the stent on an expandable portion of a catheter which is adapted to radially expand the stent;

delivering the stent to a desired location within the body lumen;


expanding said cylindrical elements with the 5 expandable portion of the catheter;

contracting the expandable portion of the catheter; and

withdrawing the catheter, leaving the expanded stent implanted in the body lumen.

ABSTRACT

The invention is directed to an expandable stent for implantation in a body lumen, such as an artery, and a method for making it from a single length of tubing. The stent consists of a plurality of radially expandable cylindrical elements generally aligned on a common axis and interconnected by one or more interconnective elements. The individual radially expandable cylindrical elements consist of ribbon-like material disposed in an undulating pattern. Portions of the expanded stent project outwardly into engagement with the vessel wall to more securely attach the stent.







FIG. 7







FIG. 10



TULWIDER PATTON LEE & UTEC Docket No. ACS 35765 Inventors: Lau et al. Page 4 of 4





FIG.13



F1G.14

DECLARATION AND POWER OF ATTORNEY FOR PATENT APPLICATION

As the below named inventors, we hereby declare that:

Our residences, post office addresses and citizenships are as stated below next to our names,

We believe we are original, first and joint inventors of the subject matter which is claimed and for which a patent is sought on the invention entitled EXPANDABLE STENTS AND METHOD FOR MAKING SAME, the specification of which (check one)

		is attached hereto	
		XX was filed on J	uly 28, 1994
		Application Serial No	8/281,790
and	was	amended on (or amended throu	gh)(if applicable)

We hereby state that we have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment(s) referred to above.

We acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, Sec. 1.56(a).

We hereby claim foreign priority benefits under Title 35, United States Code, Sec. 119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Prior F	oreign Applic	Priority	Claimed	
NONE				
Number	Country	Day/Month/Year filed	Yes	No

We hereby claim the benefit under Title 35, United States Code, Sec. 120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, Sec. 112, we acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, Sec. 1.56(a) which occurred between the filing date of the prior application and the national or PCT international filing date of this application.

NONE
Appln. Serial No. Filing Date Status (patented, pending abandoned)

We hereby declare that all statements made herein of our own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

We hereby appoint the following attorneys to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

CRAIG B. BAILEY, Registration No. 28,786, RICHARD A. BARDIN, Registration No. 20,365, GILBERT G. KOVELMAN, Registration No. 19,552, and JOHN S. NAGY, Registration No. 30,664. Direct all telephone calls to John S. Nagy at telephone No. (310) 824-5555.

Docket No. ACS 35765 (3803.3) Page 3 of 3

Address all correspondence to:

FULWIDER, PATTON, LEE & UTECHT 10877 Wilshire Boulevard Tenth Floor Los Angeles, California 90024

Full name of first inventor: Lilip Lau
Inventor's signature:
Date:
Residence: Sunnyvale, California
Citizenship: United States of America
Post Office Address: 1132 South Sage Court Sunnyvale, California 94087
Full name of second inventor: William M. Hartigan
Inventor's signature:
Date:, 1994
Residence: Fremont, California
Citizenship: United States of America
Post Office Address: 4547 Renato Court Fremont, California 94536
Full name of third inventor: John J. Frantzen
Inventor's signature:
Date:, 1994
Residence: Copperopolis, California
Citizenship: United States of America
Post Office Address: 424 Poker Flat Road Copperopolis California 95229

DECLARATION AND POWER OF ATTORNEY FOR PATENT APPLICATION

As the below named inventors, we hereby declare that:

Our residences, post office addresses and citizenships are as stated below next to our names,

We believe we are original, first and joint inventors of the subject matter which is claimed and for which a patent is sought on the invention entitled EXPANDABLE STENTS AND METHOD FOR MAKING SAME, the specification of which (check one)

o
July 28, 1994
08/281,790
ough)
(if applicable)
_

We hereby state that we have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment(s) referred to above.

We acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, Sec. 1.56(a).

We hereby claim foreign priority benefits under Title 35, United States Code, Sec. 119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)			Priority	Claimed
NONE	·			
Number	Country	Day/Month/Year filed	Yes	No

Page 2 of 3

We hereby claim the benefit under Title 35, United States Code, Sec. 120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, Sec. 112, we acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, Sec. 1.56(a) which occurred between the filing date of the prior application and the national or PCT international filing date of this application.

NONE
Appln. Serial No. Filing Date Status (patented, pending abandoned)

We hereby declare that all statements made herein of our own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

We hereby appoint the following attorneys to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

CRAIG B. BAILEY, Registration No. 28,786, RICHARD A. BARDIN, Registration No. 20,365, GILBERT G. KOVELMAN, Registration No. 19,552, and JOHN S. NAGY, Registration No. 30,664. Direct all telephone calls to John S. Nagy at telephone No. (310) 824-5555.

Address all correspondence to:

FULWIDER, PATTON, LEE & UTECHT 10877 Wilshire Boulevard Tenth Floor Los Angeles, California 90024

Full name of first inventor: Lilip Lau
Inventor's signature:
Date:, 1994
Residence: Sunnyvale, California
Citizenship: United States of America
Post Office Address: 1132 South Sage Court Sunnyvale, California 94087
Full name of second inventor: William M. Hartigan
Inventor's signature:
Date: 7-27-, 1994
Residence: Fremont, California
Citizenship: United States of America
Post Office Address: 4547 Renato Court Fremont, California 94536
Full name of third inventor: John J. Frantzen
Inventor's signature:
Date:, 1994
Residence: Copperopolis, California
Citizenship: United States of America
Post Office Address: 424 Poker Flat Road Copperopolis California 95228

DECLARATION AND POWER OF ATTORNEY FOR PATENT APPLICATION

As the below named inventors, we hereby declare that:

Our residences, post office addresses and citizenships are as stated below next to our names,

We believe we are original, first and joint inventors of the subject matter which is claimed and for which a patent is sought on the invention entitled EXPANDABLE STENTS AND METHOD FOR MAKING SAME, the specification of which (check one)

		is attached hereto	
		XX was filed on July 28, 1994	
		Application Serial No. 08/281,790	
and	was	amended on (or amended through)(if applicable)	

We hereby state that we have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment(s) referred to above.

We acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, Sec. 1.56(a).

We hereby claim foreign priority benefits under Title 35, United States Code, Sec. 119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Prior 1	Foreign Appli	cation(s)	Priority	Claimed
NONE				
Number	Country	Day/Month/Year filed	Yes	No

We hereby claim the benefit under Title 35, United States Code, Sec. 120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, Sec. 112, we acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, Sec. 1.56(a) which occurred between the filing date of the prior application and the national or PCT international filing date of this application.

NONE
Appln. Serial No. Filing Date Status (patented, pending abandoned)

We hereby declare that all statements made herein of our own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

We hereby appoint the following attorneys to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

CRAIG B. BAILEY, Registration No. 28,786, RICHARD A. BARDIN, Registration No. 20,365, GILBERT G. KOVELMAN, Registration No. 19,552, and JOHN S. NAGY, Registration No. 30,664. Direct all telephone calls to John S. Nagy at telephone No. (310) 824-5555.

Address all correspondence to:

FULWIDER, PATTON, LEE & UTECHT 10877 Wilshire Boulevard Tenth Floor Los Angeles, California 90024

Full name of first inventor: Lilip Lau
Inventor's signature:
Date:, 1994
Residence: Sunnyvale, California
Citizenship: United States of America
Post Office Address: 1132 South Sage Court Sunnyvale, California 94087
Full name of second inventor: William M. Hartigan
Inventor's signature:
Date:, 1994
Residence: Fremont, California
Citizenship: United States of America
Post Office Address: 4547 Renato Court Fremont, California 94536
Full name of third inventor: John J. Frantzen
Inventor's signature:
7/ / / 1994
Residence: Copperopolis, California
Citizenship: United States of America
Post Office Address: 424 Poker Flat Road Conneronalis California 05228